

MAPEX NYLON ENGINEERING PLASTICS

Properties	UNIT	Test Method	Mapex A0050FN
Mechanical			
抗張強度 Tensile Str, Yield	Psi(Mpa)	D-638	11000(76)
斷裂伸長率 Tensile Elongation, Break	%	D-638	8.5
彎曲強度 Flexural Strength	Psi(Mpa)	D-790A	18000(124)
彎曲彈性率 Flexural Modulus	Psi(Mpa)	D-790A	480000(3308)
IZOD衝擊強度 Izod Impact Strength, Notched	ft-lb/in (J/m) 23°C -30°C	D-256	0.8(43) -
硬度 Rockwell Hardness	R-Scale	D-785	115
Thermal			
融點 Melting Point	°C	D-789	260
熱變形溫度 Heat Deflection Temperature	°C 66 psi(0.45Mpa) 264 psi(1.82Mpa)	D-648	- 110
線膨脹係數 Coefficient of Thermal Expansion	E-5 1/°C	D-696	7
熾熱電線耐燃試驗 Glow Wire Test	°C	IEC 695-2-1	-
Electrical			
介電強度 Dielectric Strength	kv/mm	D-149	-
體積電阻 Volume Resistivity	ohm-cm	D-257	-
耐電弧 Arc Resistance	sec	D495	-
Other			
比重 Specific Gravity	-	D-792	1.16
流動指數 Melt Flow Index	g/10min °C/ Kg)	D-1238	-
成型收縮率 Mold Shrinkage, Flow	% 3mm	D-955	-
吸水率 Water Absorption	% 23°C, 24hr	D-570	0.3
Flammability			
燃燒性 Flammability	1/8" 1/16" 1/32"	UL-94	V-0
附註 Remark	Unreinforced Polyamide 66 , Flame Retardant , Non-Halogen , RoHS certification		

*Typical properties can be subject to change without further notice.

ISO9001 / ISO14001 / IECQ QC080000 ASSURANCE

GINAR TECHNOLOGY CO., LTD.

Marketing Communications Department TAIWAN
Phone +886-3-3868820 Fax +886-3-3863587

Http: // www.ginar.com.tw
E-mail: ginar@ ginar.com.tw

單位換算	抗張強度, 彎曲強度, 彎曲彈性率	IZOD 衝擊強度
	1psi=0.0703 kg/cm ²	1 ft-lb/in =5.45 kg-cm/cm
	1Mpa=10.2 kg/cm ²	1J/m=0.102 kg-cm/cm